

SABIC® PP QR6731K

POLYPROPYLENE RANDOM COPOLYMER

DESCRIPTION

SABIC® PP QR6731K is specially developed for producing injection molded & ISBM articles with very high clarity at low processing temperatures. This grade contains advance clarifier and anti-static agent. SABIC® PP QR6731K has following features: Consistent processability; Good stiffness; Exceptional clarity; Lower energy consumption and less cycle time due to low processing temperatures.

TYPICAL APPLICATIONS

SABIC® PP QR6731K can be used for clear housewares items, caps & closures, food containers, bottles (ISBM), lids and CD boxes.

TYPICAL PROPERTY VALUES

Revision 20170706

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 230 °C and 2.16kg	25	g/10 min	ASTM D1238
Density			
at 23°C	905	kg/m ³	ASTM D790
MECHANICAL PROPERTIES			
Flexural Modulus (1% Secant) ⁽¹⁾			
	1050	MPa	ASTM D790 A
Izod Impact Strength			
notched, at 23°C	65	J/m	ASTM D256
Rockwell Hardness, R-Scale			
	94	-	ASTM D785
FILM PROPERTIES			
Tensile Properties			
stress at yield	28	MPa	ASTM D638
strain at yield	12	%	ASTM D638
THERMAL PROPERTIES			
Vicat Softening Temperature			
	127	°C	ASTM D1525
Heat deflection temperature			
at 455kPa	83	°C	ASTM D648

(1) Based on injection molded specimens

PROCESSING CONDITIONS



Typical processing conditions for QR6731K are:

Barrel temperature range: 190 - 220°C

Mold Shrinkage: 1.2 - 2.0% depending on wall thickness and processing conditions.

Mold Temperature: Normally 15 - 40°C, up to 65°C for thick parts.

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

SABIC® PP QR6731K is suitable for food contact application. Detailed information is provided in relevant documents / certificates and for additional specific information please contact SABIC local representative.

DISCLAIMER: This product is not intended for and must not be used in any pharmaceutical / medical applications.

STORAGE AND HANDLING

Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

DISCLAIMER

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by Saudi Arabia Basic Industries Corporation.